

## Forward - Article passport



Article with a woolly look and full grip.

Available from stock in a wide range of contemporary and commercial colours.

## Product characteristics

Productgroup	flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery, drapery
Composition faceside	50%WO 30%LI 20%PA
Statistic Code	51119098
Dyeing method	yarn dyed
Available colours	23

## Durability specifications

Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				DRY	WET	DGM	DGM+	
Abrasion Resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 12.000	min. 16.000	A
Pilling	DIN EN ISO 12945-2:2000-11, 2000 cycles	CTL	grade	3-4		min. 3-4	min. 4	C
Colour fastness to light	DIN EN ISO 105-B02:2014-11, Process 3, exposure level 5							
	light colours	CTL	grade	4		min. 4	min. 5	C
	middle colours	CTL	grade	4-5		min. 4	min. 5	B-C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324, Schedule 4 part I, Ignition source 0: cigarette							
		Centexbel		passed				
Ignitability (match test)	DIN EN ISO 1021-1:2014, Source: Smouldering cigarette							
		Centexbel		passed				
	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324, Schedule 4 part I, Ignition source 1: Match flame equivalent							
		Centexbel		passed				
	DIN EN ISO 1021-2:2014, Source: Match flame equivalent							

## Processing specifications

Minimum workable width in centimeters	± 148
Roll length in meters	± 50
Material weight in grams per linear meter	± 550

Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	436	544	min. 350	min. 400	B/B
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	35,5	34,4	min. 25	min. 30	B/B
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07, Load 180 N	CTL	mm	3,0	3,0	max. 5	max. 4	A/A
Chemical substances	REACH	Centexbel		passed				

## Cleaning specifications



**Textaafoam**  
creativity in fabrics

Textaafoam b.v.  
La Défense 11 | 5026 SC Tilburg  
P.O. Box 12 | 5050 AA Goirle  
The Netherlands

T +31(0)13 534 5934  
F +31(0)13 534 7586  
E info@textaafoam.nl  
www.textaafoam.nl